

→ step – Protective Slabs / Walkway Slabs

Tender Specification

No. 9220 - R - 07

Issue: Feb. 2011

Item	Quantity	Description	Unit Price [€]	Price [€]
		<p>KRAITEC® step is a protective surfacing and walkway slab (e.g. for inspection walkways) used on flat roofs and green roofs as well as balconies and terraces.</p> <p>Additional specialty versions: KRAITEC® step plus with geotextile underlay KRAITEC® step safe with anti-slip texturing KRAITEC® step plus-safe with anti-slip texturing and geotextile underlay</p> <p>The slabs are fabricated from polyurethane-bonded recycled tyre material. They have an E_{fl} fire resistance rating (normal fire resistance) according to EN 13501 Part 1 and a B_{roof}(t1) fire resistance rating according to DIN EN 13501-5. Their area weight is approx. 20.8 kg/m² (21.1 kg/m² for versions incorporating geotextile underlay).</p> <p>Installation to be carried out as specified in manufacturer's installation instructions.</p> <p>Manufacturer: Gummiwerk KRAIBURG RELASTEC GmbH Fuchsbergerstr. 4, D-29410 Salzwedel / Germany Tel: +49/8683-701-167, Fax: +49/8683-701-4177</p>		

→ step – Protective Slabs / Walkway Slabs

Tender Specification

No. 9220 - R - 07

Issue: Feb. 2011

Item	Quantity	Description	Unit Price [€]	Price [€]
1.		m ² KRAITEC® step (or specialty version) slabs, length l = 500 mm, width w = 500 mm, thickness t = 30 mm. Available colours: red, green, grey, black. To be supplied, unloaded from transport lorry and brought to the point of installation.		
2.		m ² installation of KRAITEC® step (or specialty version) slabs including interconnection with integrated connector pins and including appropriate securing in accordance with DIN EN 1991- 1-4 against wind uplift.		
3.		alternative: m ² separating layer (required material and thickness to be specified/approved by roofing membrane manufacturer) to be supplied and installed. Materials: _____ Labour: _____		

DISCLAIMER:

The information and data given above are provided to the best of our knowledge based on our test results and experience to date. However, due to the multitude of possible applications and storage, processing and site conditions which are beyond our control, this information and data shall not be construed as a guarantee of any kind for installed KRAITEC® products or their performance in an intended application. Users are advised to carry out their own tests to evaluate suitability for their specific application.

Our Technical Service department will gladly provide further information or assistance as required.

This data sheet is not subject to an update service. All information and data are provided without engagement on our part.

Please visit www.kraiburg-relastec.de to download the currently valid version.